

Product Information



Ebonite H-150T

DESCRIPTION

Cross Ebonite Oils are asphaltic lubricant or compound for in the tyre industry and rubber compounding. The Ebonite series can also be used for multiple applications including greases, open gears, chains and inks applications.

TEST NAME	TEST METHOD	SPECIFICATIONS		
		Minimum	Maximum	Typical
Viscosity, cSt @ 40° C	D-445	-	-	552.9
Viscosity, cSt @ 100° C	D-445	-	-	24.6
Viscosity, SUS @ 100° F	D-2161	-	-	3050
Viscosity, SUS @ 210° F	D-2161	90	140	122.5
Gravity, API, 60° F	D-4052	17.5	22.3	20.3
Specific Gravity, 60/60° F	D-1250	0.92	0.95	0.932
Pounds per Gallon @ 60° F	D-1250	-	-	7.762
Flash, COC, °C (°F)	D-92	220 (430)	-	240 (460)
Pour Point, °C (°F)	D-97	-	-9 (+15)	-13 (+9)
Color	D-1500	-	-	BLACK
Fractions by Clay-Gel Absorption	D-2007			
Asphaltenes			-	1.0
Polars			-	5.48
Aromatics			-	37.49
Saturates			60	56.03
DMSO Extraction, %	IP-346	-	3.0	2.2
PAH			10 ppm	
Benzo (a) anthracene				0.204
Benzo (a) pyrene				0.579
Benzo (b) fluorantene				0.585
Benzo (j) fluoranthene				0.585
Benzo (k) fluoranthene				ND
Benzo (a) phenanthrene				0.475
Dibenzo (a,h) anthracene				0.197
Benzo (e) pyrene				4.957

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

Health And Safety Information See separate Safety Data Sheets available on request.

Cross™ and **Ebonite™** are trademarks of Cross Oil Refining & Marketing, Inc.. All other marks are property of their respective owners.

Product Information

CROSS OIL REFINING & MARKETING, INC.

SMACKOVER, AR 71762 ■ USA ■ PHONE 800 864-6275 ■ www.crossoil.com
