

Product Information



Ebonite H-200

DESCRIPTION

Cross Ebonite Oils are asphaltic lubricant or compound for in the tyre industry and rubber compounding. The Ebonite series can also be used greases, open gears, chains and inks applications.

TEST NAME	TEST METHOD	SPECIFICATIONS		
		Minimum	Maximum	Typical
Viscosity, cSt @ 40° C	D-445			
Viscosity, cSt @ 100° C	D-445	40.9	45.2	43
Viscosity, SUS @ 100° F	D-2161			
Viscosity, SUS @ 210° F	D-2161	200	220	210
Viscosity Index	D-2270			40
Gravity, API, 60° F	D-4052	15.2	18.6	16.9
Specific Gravity, 60/60° F	D-1250			0.9535
Pounds per Gallon @ 60° F	D-1250			7.941
Flash, COC, °C (°F)	D-92	257 (495)		266 (510)
Pour Point, °C (°F)	D-97		-1 (+30)	-7 (+20)
Color	D-1500			BLACK
Clay-Gel Analysis	D-2007			
Asphaltenes				1.65
Polars				19.26
Aromatics				36.94
Saturates				42.15
Sulfur, % wt.	D-4294			0.859
Volatility, 22 hrs @ 225°F	D-972			<0.1

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

Health And Safety Information See separate Material Safety Data Sheets available on request.

CROSS OIL REFINING & MARKETING, INC.

SMACKOVER, AR 71762 ■ USA ■ PHONE 800 864-6275 ■ www.crossoil.com