

Product Information



Ebonite H-240

DESCRIPTION

Cross Ebonite Oils are asphaltic lubricant or compound for in the tyre industry and rubber compounding. The Ebonite series can also be used for multiple applications including greases, open gears, chains and inks applications.

TEST NAME	TEST METHOD	SPECIFICATIONS		
		Minimum	Maximum	Typical
Viscosity, cSt @ 40° C	D-445	1182.4	1599.7	1391.30
Viscosity, cSt @ 100° C	D-445	-	-	49.18
Viscosity, SUS @ 100° F	D-2161	5477.4	7410.5	6445.1
Viscosity, SUS @ 210° F	D-2161	-	-	230.3
Gravity, API, 60° F	D-4052			16.5
Specific Gravity, 60/60° F	D-4052	-	-	0.9563
Pounds per Gallon @ 60° F	D-4052			7.964
Flash, COC, °C (°F)	D-92	230 (445)	-	246 (474.8)
Pour Point, °C (°F)	D-97	-	-1 (30)	-9 (16)
Color	D-1500	-	-	BLACK
Aniline Point, °C (°F)	D-611	-	-	90.6 (195.1)
Viscosity-Gravity Constant	D-2501	-	-	0.8807
Refractive Index @ 20 °C	D-1747	-	-	1.543
Neutralization Number	D-974		0.05	0.01
Ring Carbon Distribution				
Aromatic Carbon Atoms, %Ca	D-2140	-		34
Naphthenic Carbon Atoms, %Cn	D-2140		-	12
Paraffinic Carbon Atoms, %Cp	D-2140			54
Fractions by Clay-Gel Absorption				
Polar Compounds, Mass %	D-2007			24.1
Aromatics, Mass %	D-2007	-	-	33.5
Saturates, Mass %	D-2007			42.4
Sulfur, Mass %	D-4294	-	0.05	0.01
DMSO Extraction, %	IP-346	-	3.0	< 3.0

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

Health And Safety Information See separate Safety Data Sheets available on request.

Cross™ and **Ebonite™** are trademarks of Cross Oil Refining & Marketing, Inc.. All other marks are property of their respective owners.