

# CORSOL 2400

## PROCESS OILS

Corsol Series are severely hydro treated naphthenic process oils manufactured from select crude streams. Corsol Series oil offer low pour point good solvency and color stability. They are ideal for production blending, adhesives, plastics and extended rubber.

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL
		Min	Max	
<b>Physical Properties</b>				
Viscosity, cSt @ 40° C	D-445	402.2	470.5	448.0
Viscosity, cSt @ 100° C	D-445	-	-	22.5
Viscosity, SUS @ 100° F	D-2161	-	-	2452.9
Viscosity, SUS @ 210° F	D-2161	-	-	112.9
Gravity, API, 60° F	D-4052	-	-	20.0
Specific Gravity, 60/60° F	D-1250	-	-	0.9340
Pounds per Gallon @ 60° F	D-1250	-	-	7.7805
Flash, COC, C° (F°)	D-92	217 (420)	-	244 (471)
Pour Point, C° (°F)	D-97	-	-	-10 (+14)
Color	D-1500	-	4.0	L 3.5
Aniline Point, C° (°F)	D-611	-	-	99 (210)
Molecular Weight	D-2502	-	-	525
Refractive Index @ 20° C	D-1747	-	-	1.511
Refractivity Intercept	D-2159	-	-	1.047
Ring Carbon Distribution		-	-	
Aromatic Carbon Atoms, %Ca	D-2140	-	-	19
Naphthenic Carbon Atoms, %Cn	D-2140	-	-	24
Paraffinic Carbon Atoms, %Cp	D-2140	-	-	57
Fractions by Clay-Gel Absorption		-	-	
Asphaltenes, Mass %	D-2007	-	-	0
Polar Compounds, Mass %	D-2007	-	-	3.2
Aromatics, Mass %	D-2007	-	-	40.4
Saturates, Mass %	D-2007	-	-	56.4
Sulfur, Mass %	D-4294	-	-	0.20
UV Absorptivity, 260 NM	D-2008	-	-	7.2
Volatility, 22 hr/225° F, % Mass	D-972	-	-	0.3
DMSO Extract, wt.%	IP-346	-	3.0	< 3.0

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

**Health And Safety Information** See separate Safety Data Sheets available on request.

Cross™ and Corsol™ are trademarks of Cross Oil Refining & Marketing, Inc.. All other marks are property of their respective owners.

**Cross Oil Refining & Marketing, Inc.**

Smackover, AR 71762 | USA | Phone 800 864-6275 | [www.crossoil.com](http://www.crossoil.com)

Product Data Sheet Revision 2412