

Product Information



Ebonite OGL-330

DESCRIPTION

Cross Ebonite Oils are asphaltic lubricant or compound for in the tyre industry and rubber compounding. The Ebonite series can also be used greases, open gears, chains and inks applications.

| TEST NAME | TEST METHOD | SPECIFICATIONS | | |
|-------------------------------|-------------|----------------|---------|----------|
| | | Minimum | Maximum | Typical |
| Viscosity, cSt @ 40° C | D-445 | | | |
| Viscosity, cSt @ 100° C | D-445 | 300 | 360 | 328.45 |
| Viscosity, SUS @ 100° F | D-2161 | | | |
| Viscosity, SUS @ 210° F | D-2161 | 1490 | 1790 | 1632 |
| Viscosity Index | D-2270 | | | 50 |
| Gravity, API, 60° F | D-4052 | 10 | 15 | 12.5 |
| Specific Gravity, 60/60° F | D-1250 | | | 0.9826 |
| Pounds per Gallon @ 60° F | D-1250 | | | 8.183 |
| Flash, COC, °C (°F) | D-92 | 270(520) | | 275(530) |
| Pour Point, °C (°F) | D-97 | | | +24(+75) |
| Color | D-1500 | | | BLACK |
| Clay-Gel Analysis | D-2007 | | | |
| Asphaltenes | | | | 5.73 |
| Polars | | | | 29.41 |
| Aromatics | | | | 29.95 |
| Saturates | | | | 34.91 |
| Sulfur, % wt. | D-4294 | | | 0.898 |
| Volatility, 22 hrs @ 225°F | D-972 | | | <0.1 |
| Timken OK Load, kg w/ solvent | D-2782 | 13.6 | | > 13.8 |

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

Health And Safety Information See separate Material Safety Data Sheets available on request.

CROSS OIL REFINING & MARKETING, INC.

SMACKOVER, AR 71762 ■ USA ■ PHONE 800 864-6275 ■ www.crossoil.com