

## Product Information



# Cross L-2800

### DESCRIPTION

**Cross L Series** are severely hydro treated naphthenic process oils manufactured from select crude streams. L Series oil offer low pour point good solvency and color stability. They are ideal for production blending, adhesives, plastics and extended rubber.

TEST NAME	TEST METHOD	SPECIFICATIONS		
		Minimum	Maximum	Typical
Viscosity, cSt @ 40° C	D-445			500.83
Viscosity, cSt @ 100° C	D-445	22.9	25.1	23.25
Viscosity, SUS @ 100° F	D-2161			2756
Viscosity, SUS @ 210° F	D-2161			116.4
Gravity, API, 60° F	D-4052	19.3	22.3	21.0
Specific Gravity, 60/60° F	D-1250			0.9279
Pounds per Gallon @ 60° F	D-1250			7.727
Flash, COC, C° (F°)	D-92	240 (465)		252 (485)
Pour Point, C° (°F)	D-97		+2 (+35)	-7 (+20)
Color	D-1500		4.0	2.5
Aniline Point, C° (°F)	D-611			100 (212)
Viscosity-Gravity Constant	D-2501			0.855
Molecular Weight	D-2502			550
Refractive Index @ 20° C	D-1747			1.512
Refractivity Intercept	D-2159			1.047
Aromatic Carbon Atoms, %Ca	D-2140			19
Naphthenic Carbon Atoms, %Cn	D-2140			28
Paraffinic Carbon Atoms, %CP	D-2140			53
Asphaltenes, Mass %	D-2007			0.0
Polar Compounds, Mass %	D-2007			3.6
Aromatics, Mass %	D-2007			40.7
Saturates, Mass %	D-2007			55.7
Sulfur, Mass %	D-4294			0.15
UV Absorptivity, 260 NM	D-2008			7.5
Volatility, 22 hr/225° F, % Mass	D-972			0.2
DMSO Extract, wt.%	IP-346		3.0	< 3.0

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

**Health And Safety Information** See separate Material Safety Data Sheets available on request.

### CROSS OIL REFINING & MARKETING, INC.

SMACKOVER, AR 71762 ■ USA ■ PHONE 800 864-6275 ■ [www.crossoil.com](http://www.crossoil.com)