



CROSS TRANS 206

ELECTRICAL OILS

CrossTrans 206 is a specially processed electrical insulating oil produced from severely hydrotreated naphthenic base oils to assure high electrical resistance. It is formulated with an oxidation inhibitor to provide excellent oxidative stability. CrossTrans 206 meets the requirements of a Type II electrical insulating oil. It has been reviewed and approved by major regional and provincial power utilities and commonly used in transformers, circuit breakers, oil filled switches and medical X-ray equipment.

PERFORMANCE:

CrossTrans 206 complies fully with the following specifications:

- ANSI / ASTM D-3487, Type II
- Doble TOPS-884, Inhibited Type II
- BS 148:1984, Class IIA (Inhibited)
- CAN/CSA-C50-23, Type II (Class B)
- NEMA TR-P8-1975

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL
Physical Properties		Min	Max	
Aniline Point, °C	D-611	63	-	72
ASTM Color	D-1500	-	0.5	L 0.5
Flash Point, °C	D-92	145	-	153
Interfacial Tension @ 25°C, dynes/cm	D-971	40	-	49
Pour Point, °C	D-97	-	-40	-51
Specific Gravity, 15°C/15°C; kg/m3	D-1298	-	0.910	0.8956
Viscosity, cSt (SUS):				
@ 100 °C			3.0 (36)	2.37
@ 40 °C	D-445	-	12.0 (66)	9.47
@ 0 °C			76.0 (350)	58.1
@ -40 °C			6000	2700
Visual Examination	D-1524	Clear and Bright	-	Clear and Bright
Dielectric Breakdown Voltage,60 Hz:				
Disc electrodes, kV	D-877	Report	-	42
Dielectric Breakdown Voltage,60 Hz:				
VDE Electrode, kV	D-1816	35	-	42
Dielectric Breakdown Impulse				
Impulse Cond. @25C, 1-in (25.4mm) gap	D-3300	145	-	160
Gassing Tendency, uL/min	D-2300B	-	+30	-10

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

Health And Safety Information See separate Safety Data Sheets available on request.

Cross™ and CrossTrans™ are trademarks of Cross Oil Refining & Marketing, Inc., All other marks are property of their respective owners.



CROSS TRANS 206

ELECTRICAL OILS

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL
Physical Properties		Min	Max	
Power Factor @ 60 Hz, %, max				
@ 25°C	D-924	-	0.05	0.01
@ 100°C			0.30	0.03
Water, ppm	D-1533	-	35	5
Neutralization Number, mg KOH/g	D-974	-	0.03	< 0.01
Corrosive Sulphur	D-1275	Non-corrosive	-	Non-corrosive
PCB Content, ppm	D-4059	Not detectable	-	ND
Oxidation Stability @ 72 Hours				
% Sludge, by Mass	D-2440	-	0.15	< 0.01
Total Acid Number mg KOH/g			0.30 Maximum	< 0.01
Oxidation Stability @ 164 Hours		-		
% Sludge, by Mass	D-2440	-	0.20 Maximum	0.02
Total Acid Number mg KOH/g			0.40	0.17
Rotating Bomb, minutes	D-2112	195		290
Oxidation Inhibitor, % Mass	D-2668	-	0.30	0.25
DMSO Extract, wt.%	IP-346	-	3.0	< 1.0

Note: Crosstrans 206 meets the requirements for IEC 60296 with the exception for IEC 61125 acid number and % sludge content following the 500 hour oxidation test.

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

Quality and life of transformer oils depend upon the adherence to prescribed norms while in storage and during handling. A high level of caution is required to maintain the quality of transformer oil because of its high sensitivity to even minute contamination.

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

Health And Safety Information See separate Safety Data Sheets available on request.

Cross™ and CrossTrans™ are trademarks of Cross Oil Refining & Marketing, Inc., All other marks are property of their respective owners.