



# EBONITE H-150 E

## BLACK OILS

Ebonite Oils are asphaltic lubricant or compound for in the tyre industry and rubber compounding. The Ebonite series can also be used greases, open gears, chains and inks applications.

TEST DESCRIPTION	TEST METHOD	SPECIFICATIONS		TYPICAL	
Physical Properties		Min	Max		
	Viscosity, cSt @ 40° C	D-445	-	-	719.9
	Viscosity, cSt @ 100° C	D-445	-	-	29
	Viscosity, SUS @ 100° F	D-2161	3750	4155	3992
	Viscosity, SUS @ 210° F	D-2161	-	-	143.3
	Gravity, API, 60° F	D-4052	16	21	18.5
	Specific Gravity, 60/60° F	D-1250	-	-	0.944
	Pounds per Gallon @ 60° F	D-1250	-	-	7.858
	Flash, COC, °C (°F)	D-92	227	-	260
	Pour Point, °C (°F)	D-97	-	-	0
	Color	D-1500	-	-	BLACK
	Aniline Point	D-611	-	-	89 C
	Sulfur, Mass	D-4294	-	-	0.61%
	DMSO Extraction, %	IP-346	-	3.0	2.2

The information on this Product Data Sheet is believed to be accurate and is typical of current production. Specifications are subject to change without notice.

**Health And Safety Information** See separate Safety Data Sheets available on request.

Cross™ and Ebonite™ are trademarks of Cross Oil Refining & Marketing, Inc.. All other marks are property of their respective owners.

**Cross Oil Refining & Marketing, Inc.**

Smackover, AR 71762 | USA | Phone 800 864-6275 | [www.crossoil.com](http://www.crossoil.com)

Product Data Sheet Revision 09/2023